

TECHNICAL SPECIFICATIONS

COLORPAN Harmonized Standard: EN 13986/EN 622-5

TECHNICAL DATA	TEST STANDARD	UNIT OR FEATURE	THICKNESS RANGE						
			2,5<t≤4	4<t≤6	6<t≤9	9<t≤12	12<t≤19	19<t≤30	30<t≤45
DENSITY ^{*1}	EN 323	kg/m ³	Specific to plant						
INTERNAL BOND	EN 319	N/mm ²	0,65	0,65	0,65	0,6	0,55	0,55	0,50
BENDING STRENGTH	EN 310	N/mm ²	23	23	23	22	20	18	17
MODULUS OF ELASTICITY	EN 310	N/mm ²	*	2700	2700	2500	2200	2100	1900
SWELLING 24 H	EN 317	%	35	30	17	15	12	10	8
SCREW HOLD EDGE	EN 320	N	> 700 (for t > 15 mm)						
SAND CONTENT	EN 3340	%	< 0.05						
MOISTURE CONTENT	EN 322	%	4 - 11						
FORMALDEHYDE RELEASE	EN 12460-5	mg/100gr	≤8 (E1), >8 to ≤ 30 (E2)						
	EN 12460-1	mg/m ³ air	≤ 0,062 (E0) / ≤ 0,124 (E1)						

CONTROL CRITERIA	TEST STANDART	UNIT OR FEATURE	THICKNESS RANGE						
			2,5<t≤4	4<t≤6	6<t≤9	9<t≤12	12<t≤19	19<t≤30	30<t≤45
DENSITY	EN 323	%	±7						
THICKNESS (SANDED)	EN 622-1	mm	±0.20					±0.3	
WIDTH LENGTH	EN 324	mm	±5						
EDGE SQUARENESS	EN 622-1	mm/m	±2						

As an official trademark of Kastamonu, **Colorpan** boards are raw **MDF** based boards. This type of boards are especially used for furniture, interior decoration, wall&floor covering, kitchen, doors, bathroom, decorative panels and fair stands. Unlike coated, polished or lacquered surfaces, it has a natural-looking surface texture. Since they're self-colored, it is very easy to repair. Every type of finishing can be applied. Suitable for polishing.

***1 Density:** The density is not exactly specified because of the market variabilities. In order to get exact value of the density you are advised to contact the relevant Sales Executive.

Note 1: This document may be modified at any time by the company without any express obligation to send any updated edition to all original recipients. To verify that you have the latest edition available, you are advised to contact the relevant sales executive.

Note 2: For current EN document / document scope, it is recommended to contact the relevant sales executive.